

SCIK MONOMANO

Super-washable, anti-mold, sanitizer, acrylic paint, for internal and external supports

DESCRIPTION

SCIK MONOMANO is a super-washable acrylic paint, characterized by an exceptional filling power. Moreover the high quality raw materials give an excellent coverage related to a high metric yield. SCIK MONOMANO prevents the formation of molds and fungal growth on treated surfaces.

APPLICATION

New Walls:

- The surface to be treated must be dry. Conditions and thickness of the plaster layer affect the drying and hardening time, so make sure it has at least 28 days of curing time, depending on temperature.
- The substrate has to be well prepared and suitable for coating: dry plaster, not any granules from plaster.
- Level out imperfections of the internal support with RASAN STUCCO or with K-STUKK. In case of holes or micro-cracks, fill the inner walls with STUCCO TRE STELLE.
- Use the sandpaper in order to remove surface irregularities and then eliminate dust deposits.
- Treat the surface with SCIK BONIFIK in case of mold.
- Make sure the surface is dry and apply 1 coat of SCIK PURAL ACRIL insulation or FISSATIVO ACRILICO TRE STELLE.
- Proceed applying two coats of SCIK MONOMANO with brush, roller or spray, which has to be thinned up with water in the following percentages: 1st coat: approx.25-30% ; 2nd coat: approx. 20-25%.

Old Walls:

- The surface to be treated must be dry.
- Scrape off any loose flaking and poorly adhering coating, scraping and washing the surface with plenty of water or using a pressure washer.
- Proceed following the instruction of 'NEW WALL' from the third point onwards.

TECHNICAL DATA

Nature of the bond	Acrylic copolymer in water dispersion
Viscosity	
Drying Time	2 h at touch, 6-12 h complete.
Thinning	25-30% 1°mano 20-25% 2°mano
Yield	12-15m ² /Lt
Specific weight	1,657Kg/Lt
Colors	White or colored
Dry aspect	Matt
Wet aspect	
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 years (in sealed, unopened original packing)
VOC	µGr/m ³
TVOC	N/A
PH	N/A
Cleaning	Water
Packing	15LT,13LT,5LT

CHARACTERISICS

Characteristics:	Linea Scik.
Can be applied on:	Walls,Wood.
for:	Interiors ed Exteriors.
Certifications:	

TOOLS AND RELATED PRODUCTS

Tools:	Roller,Brush,Sprayer.
Related products:	RASAN STUCCO,K-STUCC,STUCCO TRE STELLE,SCIK BONIFIK,FISSATIVO TRE STELLE,SCIK PURAL ACRIL.

SAFETY INSTRUCTIONS

The product does not require any labelling under the Decree 285 of 16/7/98 and subsequent amendments and updates. Use the product in accordance with the relevant health and safety regulations of the country. Do not dispose of the containers in the environment after use; let the residues dry and treat them as special waste. For further information please refer to **SSR16**safety data sheet.

ITEM SPECIFICATION:

Super-washable and super-covering acrylic paint with opacity effect, for internal and external. Applications to be made on already prepared surfaces. SCIK MONOMANO cod.SAM01 based on copolymers in water dispersion and natural fillers, at least into 2 layers, determined in quantities by the substrate absorption. Supply and installation of material € per sqm.

NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions . The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.
- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge , however , being elements such as weather conditions, labor , tools, quality of third party products and others, not under the direct control of the Rivedil , this document does not constitute a warranty , nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document . We recommend that you always check the suitability of the product to each specific instance . This supersedes all previous editions.