

RIVEDIL[®]
EXCLUSIVE PAINT
MADE IN ITALY *By C. C.*

SCHEDA TECNICA N°62

TENNIS BETON

Plastic coating thickness for sports fields

DESCRIPTION

TENNIS BETON is a plastic coating thickness based on acrylic copolymers in emulsion and self-leveling agents, able to make the product particularly elastic, wear and weather resistant.

The product is recommended for all types of sports fields both indoors and outdoors.

APPLICATION

- The surface to be treated must be dry and free from traces of grease and dust.
- Remove any old, loose or flaking paint.
- Proceed applying one coat of ACRIL TENNIS, which has to be thinned up with water in the following percentages: approx 20-25%
- Once the base is dry, apply a coat of TENNIS BETON using a water pull or tampico brush.

colorificio
Rivedil
made in Italy

COLORIFICIO RIVEDIL di COSIMO CODARDO

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy

Tel. (+39) 0832 731293 - (+39) 0832 731273

P.IVA 01122590753

www.rivedil.com - export@rivedil.com

TECHNICAL DATA	
Nature of the bond	Acrylic copolymers in emulsion
Viscosity	
Drying Time	2 h at touch, 6-12 h complete.
Thinning	Ready to use
Yield	1-2m ² /Lt
Specific weight	1,744Kg/Lt
Colors	Red, Green, White
Dry aspect	Matt
Wet aspect	
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 years (in sealed, unopened original packing)
VOC	µGr/m ³
TVOC	N/A
PH	N/A
Cleaning	Water
Packing	14LT

CHARACTERISTICS	
Characteristics:	Linea Rivestimenti.
Can be applied on:	Walls, Wood.
for:	Esterno.
Certifications:	

TOOLS AND RELATED PRODUCTS	
Tools:	Spalter.
Related products:	ACRIL TENNIS.

SAFETY INSTRUCTIONS

The product does not require labelling under the Decree 285 of 16/7/98 and subsequent amendments and updates. Use the product in accordance with the relevant health and safety regulations of the country. Do not dispose of the containers in the environment after use; let the residues dry and treat them as special waste. For further information please refer to **SSR62** safety data sheet.

ITEM SPECIFICATION:

Water-based plastic coating thickness for sports fields. Applications to be made on the already prepared surfaces of TENNIS BETON cod.TCT01 based on acrylic copolymers in emulsion, at least 2 layers, in the quantities determined by the substrate absorption. Supply and installation of the material €..... per sqm.

NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions . The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.
- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge , however , being elements such as weather conditions, labor , tools, quality of third party products and others, not under the direct control of the Rivedil , this document does not constitute a warranty , nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document . We recommend that you always check the suitability of the product to each specific instance . This supersedes all previous editions.



COLORIFICIO RIVEDIL di COSIMO CODARDO

Via Prov.le per Veglie Km 0,500 - 73015 Salice Salentino (Le) Italy

Tel. (+39) 0832 731293 - (+39) 0832 731273

P.IVA 01122590753

www.rivedil.com - export@rivedil.com