

RULLATO

Thickness plastic coating for internal and external

DESCRIPTION

RULLATO TIPO MEDITERRANEO is a continuous wall covering, used in particular in the building sector, for protection and decoration of internal and external wall surfaces.

RULLATO TIPO MEDITERRANEO is a high wall thickness covering with coarse peel effect.

Its formulation based on special synthetic resins in water emulsion, offers to the product good water repellency and an excellent filling power.

APPLICATION

New Walls:

- The surface to be treated must be dry. Conditions and thickness of the plaster layer affect the drying and hardening time, so make sure it has at least 28 days of curing time.
- The substrate has to be well prepared and suitable for coating: dry plaster, not any granules from plaster. In case of old paint make sure there is no poor or dusty paint: remove it if necessary as well as flaking paint.
- Level out imperfections of the internal support with RASAN STUCCO or with K-STUCCO; use instead RIVENDUIT CALCE for the external support . In case of holes or micro-cracks, fill the inner walls with STUCCO TRE STELLE and the external ones with ESTERN STUCCO.
- Use the sandpaper in order to remove surface irregularities and then eliminate dust deposits.
- Apply 1 coat of SCIK PURAL ACRIL insulation or FISSATIVO ACRILICO TRE STELLE.
- Apply the special SOTTOFONDO PER RIVESTIMENTI .
- Proceed applying with roller or spatula, a coat of RULLATO TIPO MEDITERRANEO ready to use or diluted with water as necessary.

Old Walls:

- The surface to be treated must be dry.
- Scrape off any loose flaking and poorly adhering coating.
- Proceed following the instruction of 'NEW WALL' from the third point onwards.

TECHNICAL DATA	
Nature of the bond	Acrylic copolymer in aqueous emulsion
Viscosity	
Drying Time	2 h at touch, 12-24 h complete.
Thinning	Ready to use
Yield	2,000-3,000m ² /Lt
Specific weight	1,750Kg/Lt
Colors	Color chart/ peel effect
Dry aspect	Coarse peel
Wet aspect	
Storing	Max Temp. +30°C, Min T. +5°C
Stability	2 years (in sealed, unopened original packing)
VOC	µGr/m ³
TVOC	N/A
PH	N/A
Cleaning	Water
Packing	5LT,14LT
CHARACTERISICS	
Characteristics:	Linea Rivestimenti.
Can be applied on:	Walls,Wood.
for:	Interiors ed Exteriors.
Certifications:	
TOOLS AND RELATED PRODUCTS	
Tools:	Brush.
Related products:	RASAN STUCCO,K-STUCC,RIVENDUIT CALCE,STUCCO TRE STELLE,ESTERN STUCCO,SCIK PURAL ACRIL,FISSATIVO TRE STELLE.

The product does not require labelling under the Decree 285 of 16/7/98 and subsequent amendments and updates. Use the product in accordance with the relevant health and safety regulations of the country. Do not dispose of the containers in the environment after use; let the residues dry and treat them as special waste. For further information please refer to **SSR122** safety data sheet.

ITEM SPECIFICATION:

Matt thickness plastic wall coating for internal and external.

Applications to be made on already prepared surfaces of plastic wall coating for internal and external. RULLATO TIPO MEDITERRANEO cod.RM01, in quantities determinated by the substrate absorption.

Supply and installation of material € per sqm.

NOTES

- Please note that due to technical reasons caused by the tinting of the product the indicated Specific Weight of the product may differ from the Package Net Weight.
- In the original, sealed containers and in appropriate temperature conditions . The period of stability is purely indicative, and refers to the minimum stability period of the product if stored ideal conditions according to the instructions provided. If properly stored the products stability period may extend several years.
- Rivedil ensures that the information herein is provided to the best of its experience and its technical and scientific knowledge , however , being elements such as weather conditions, labor , tools, quality of third party products and others, not under the direct control of the Rivedil , this document does not constitute a warranty , nor does Rivedil authorize its agents and / or representatives to provide any kind of warranty based on the information contained in this document . We recommend that you always check the suitability of the product to each specific instance . This supersedes all previous editions.